




Slabs glass cloth faced 220 g/m² - Density 50 kg/m³



ULTIMATE mineral wool provides a unique high-performance profile : It combines safety, comfort and ease of handling.



FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire.



THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency.



SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties.



LIGHTWEIGHT

Increase insulation - reduce weight. ULTIMATE combines high fire & thermal performance with very low weight.



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES							STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	400	EN 14706
	λ _{N,R}	[W/(m·K)]	0.031	0.036	0,042	0,050	0,059	0,080	0,109	
Thermal behaviour	T	[°C]	≤ 650 by pure thermal stress (U SeaProtect Slab 40 - 90) The thickness of the insulating layer has to be correctly dimensioned so that the faced side is exposed to a maximum of 100 °C. From 150 °C on the binder starts to volatilise.							EN 14706

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Air flow resistivity	σ	[KPa· s/m ²]	Density 50 kg/m ³	[40-60]	DIN EN 29053

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Specific thermal capacity	c	kJ/(kg.K)	1.00	ISO 10456
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: ≥ 1000 °C. Non combustible according to IMO-Resolution MSC.61(67)-(FTP- Code), IMO MSC/Circ. 1120. Surface materials with low flame-spread characteristics. Homologated for shipbuilding	RESOLUTION MSC.307(88) (2010 FTP CODE)
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding. Approved for A-Class steel constructions	-
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle . V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to guideline EU97/69 Nota Q.	-
Facing	-	-	One-sided faced with glass fiber cloth with a gram weight of 220 g/m ²	-
Water vapour diffusion resistance factor	μ	-	- 1.0	-
Thermal coefficient of expansion	α	1/K	No change in dimensions within the application field.	-
Quality management	-	-	ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001	EN ISO 9001 EN ISO 14001

DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION*		
Thickness d [mm]	Length [mm]	Width b [mm]
25	1200	625
30	1200	625
50	1200	625
60	1200	625

* On some products, minimum order quantities are requested.
 ** Further dimensions on request.

